

Technical Data Sheet Tuffbond[®] 58741

December 2009

Page 1 of 1

Product Description

Hernon[®] Tuffbond[®] 58741 adhesive/sealant is a two component, 100% solid system, one to one ratio, room temperature cure system.

Typical Applications

- Tank lining
- Chemical resistant flooring
- Marine coating
- Underwater coating

Product Benefits

- Excellent resistance to organic acids and bases.
- Good mechanical properties.
- Outstanding resistance to abrasion.
- Non-critical mixing.

Typical Properties (Uncured)

Property	Part A	Part B
Base	Epoxy	Amine
Appearance	Light gray	Amber
Viscosity, 25°C, cP	850,000-1,00,000	300,000-500,000
Mix Ratio by Weight	1	1
Specific Gravity	1.41	1.02
Flash Point	See MSDS	See MSDS

Typical Properties (Cured)

Property	Value
Working Life at 22°C (100g), minutes	45 to 65
Tensile Strength, psi, ASTM D638	5700 - 7100
Hardness, Shore D, ASTM D2240	77
Coefficient of Thermal Expansion, in/in/°C ASTM D696	76 x 10 ⁻⁶
Volume Resistivity, ohm-cm, ASTM D696	7.1 x 10 ¹²
Glass Transition Temperature, (T _g) °C	71
Flash-Ignition Temp, °C, ASTM D1929	360
Spontaneous-Ignition Temperature, °C, ASTM D1929	460
Shear Strength – Aluminum, psi ASTM D1002	3200
Temperature Range	-65 to 300 °F (-53 to 149 °C)

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Storage

Tuffbond[®] 58741 should be stored in a cool, dry location in unopened containers at a temperature between 46°F to 82°F (8°C to 28°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon[®] offers a complete line of semi and fully automated dispensing equipment. Contact Hernon[®] Sales for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING[®], INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high performance adhesives and sealants is registered to the ISO 9001 Quality Standard.